



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



Publication number: **0 687 008 A2**

(12)

## EUROPEAN PATENT APPLICATION

(31) Application number: 95108620.6

(51) Int. Cl.<sup>5</sup>: H01L 23/495, H01L 21/48

(22) Date of filing: 06.06.95

(52) Priority: 06.06.94 US 254842

(43) Date of publication of application:  
13.12.95 Bulletin 95/50

(86) Designated Contracting States:  
DE FR GB

(71) Applicant: **MOTOROLA, INC.**  
1303 East Algonquin Road  
Schaumburg, IL 60196 (US)

(72) Inventor: **Ganesan**  
5972 West Gall Drive  
Chandler,

Arizona 85226 (US)  
Inventor: **Berg, Howard Martin**  
12017 North 84th Street  
Scottsdale,  
Arizona 85260 (US)

(74) Representative: **Hudson, Peter David et al**  
**Motorola**  
**European Intellectual Property**  
**Midpoint**  
**Alencon Link**  
**Basingstoke,**  
**Hampshire RG21 1PL (GB)**

(54) Method and apparatus for improving interfacial adhesion between a polymer and a metal

(57) A leadframe (11) and a method for improving adhesion of a polymer (17, 19) to the leadframe (11). The leadframe (11) has a flag (14) having a top surface (15) and a bottom surface (18), and leads (12). Microscopic locking features (31) are formed in the top surface (15) and the bottom surface (18) of flag (14) by bombarding the flag (14) with a grit material. Thus, the top and bottom surfaces (15, 18) are roughened. A semiconductor die (13) is attached to the flag (14) by a die attach material (17) and the flag (13), the semiconductor material (13), and portions of the leads (12) are encapsulated by a molding compound. The pits improve the adhesion of the die attach material (17) and the molding compound (19) to the leadframe (11).




FIG. 1




FIG. 2

EP 0 687 008 A2